

ARP-CG-60

Commercial Grade Silicone Sheet

Features:

- Low Compression Set
- Outstanding Resistance to UV, Ozone, Oxidation and Weathering
- Resistance at Extreme High and Low Temperatures
- Good Chemical Resistance

| Properties | Test Method | Typical Values |
|-----------------------------------|-----------------|------------------|
| Color | Visual | Red, Grey, Black |
| Finish | Visual | Smooth |
| Width | ASTM D751 | 36" – 60" |
| Thickness | ASTM D751 | .010" – 1" |
| Shore "A" Durometer | ASTM D2240 | 60 ± 5 |
| Tensile Strength, psi | ASTM D412 | 700 |
| Elongation, % | ASTM D412 | 300 |
| Tear Strength, ppi Die "B" | ASTM D624 | 100 |
| Temperature Range | Fahrenheit (°F) | -76 to +450 |

*The values from samples of different sizes will be different from that stated here

Availability:

- Custom Widths
- Continuous Roll Lengths
- Color Match Capabilities
- Pressure Sensitive Adhesive (PSA) Backing

The information supplied herein is based upon information currently available on the subject. The above values are typical properties and should be used only as a guide. There are no warranties, either expressed or implied, including the warranty for fitness of use or of merchantability. It is up to the end user to determine whether the material is appropriate for the intended application.