

## ARP-MS-60

### Medium Strength Grade Silicone Sheet

**Features:**

- For Medium Strength Applications
- Excellent Compression Set Resistance
- FDA Approved Ingredients
- Good Chemical Resistance
- Resistance at Extreme High & Low Temperatures
- Outstanding Resistance to UV, Ozone, Oxidation & Weathering

**Specifications:**

- ASTM D2000 M3FC607 B37
- FDA TITLE 21CFR 177.2600

***Capable of Meeting:***

A-A-59588 CL2A & CL2B GR60  
 ZZR-765 CL2A & CL2B GR60

Properties	Test Method	Typical Values
<b>Color</b>	Visual	Red, Grey, Black
<b>Finish</b>	Visual	Smooth
<b>Width</b>	ASTM D751	36" – 60"
<b>Thickness</b>	ASTM D751	.010" – 1"
<b>Shore "A" Durometer</b>	ASTM D2240	60 ± 5
<b>Tensile Strength, psi</b>	ASTM D412	1100
<b>Elongation, %</b>	ASTM D412	400
<b>Tear Strength, ppi Die "B"</b>	ASTM D624	140
<b>Temperature Range</b>	Fahrenheit (°F)	-80°F to 480°F +500°F intermittent

\*The values from samples of different sizes will be different from that stated here

**Availability:**

- Custom Widths
- Continuous Roll Lengths
- Color Match Capabilities
- Pressure Sensitive Adhesive (PSA) Backing

The information supplied herein is based upon information currently available on the subject. The above values are typical properties and should be used only as a guide. There are no warranties, either expressed or implied, including the warranty for fitness of use or of merchantability. It is up to the end user to determine whether the material is appropriate for the intended application.